

L&M SUPPLY CO., INC.

P.O. Box 640
1800 Springhead Ch. Rd.
Willacoochee, Ga. 31650

912-534-6071
800-948-7870
912-534-6254(fax)

L&M 200# Woven Stabilization

This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. We wish to advise that L&M 200 meets the following minimum average roll values:

Property	Test Method	Minimum Average Roll Value (English)
Grab Tensile	ASTM-D-4632	200 lbs
Grab Elongation	ASTM-D-4632	15%
Mullen Burst	ASTM-D-3786	460 psi
Puncture	ASTM-D-4833	95 lbs
Trapezoidal Tear	ASTM-D-4533	75 lbs
UV Resistance	ASTM-D-4355	70 % at 2500 hr
Permittivity	ASTM-D-4491	0.05 sec ⁻¹
AOS	ASTM-D-4751	40 Sieve
Flow Rate	ASTM-D-4491	4 gal/min/ft ²

L&M Bag and Supply Co., Inc. provides the woven fabric indicated above. The values listed are a result of testing conducted by an independent testing laboratory. These test results are no more than one year old when presented to the authorizing agent.

L&M SUPPLY CO., INC.

P.O. Box 640
1800 Springhead Ch. Rd.
Willacoochee, Ga. 31650

912-534-6071
800-948-7870
912-534-6254(fax)

L&M 300# Woven Stabilization

This engineered geotextile is stabilized to resist degradation due to ultraviolet exposure. It is resistant to commonly encountered soil chemicals, mildew and insects, and is non-biodegradable. We wish to advise that L&M 300 meets the following minimum average roll values:

Property	Test Method	Minimum Average Roll Value (English)
Grab Tensile	ASTM-D-4632	315 lbs
Grab Elongation	ASTM-D-4632	15%
Mullen Burst	ASTM-D-3786	604 psi
Puncture	ASTM-D-4833	140 lbs
Trapezoidal Tear	ASTM-D-4533	120 lbs
UV Resistance	ASTM-D-4355	70 % at 2500 hr
Permittivity	ASTM-D-4491	0.05 sec ⁻¹
AOS	ASTM-D-4751	40 Sieve
Flow Rate	ASTM-D-4491	4 gal/min/ft ²

L&M Bag and Supply Co., Inc. provides the woven fabric indicated above. The values listed are a result of testing conducted by an independent testing laboratory. These test results are no more than one year old when presented to the authorizing agent.